

▶ Zerust[®] Axxatec[™] 80C

Zerust Axxatec 80C is a water-based rust preventative liquid that protects ferrous metals for up to one year under shelter. It can be applied by spray, brush or dip and leaves a clear and dry to the touch protective coating. Safe for painted, rubber and plastic materials.

Zerust Axxatec 80C is a water-based rust preventative liquid concentrate that may be diluted from 2% to 7.5% per the application. This aqueous-based corrosion inhibitor system protects ferrous metals via proven Zerust Integrated Corrosion Technologies (ICT[®]). Use Axxatec 80 to protect bare ferrous metals such as cast iron, steel and its alloys during shipping, storage and assembly.

Axxatec 80 forms a clear, thin, dry-to-touch coating and is safe for use on painted surfaces, rubber seals, and plastics. It provides up to one year protection indoors or in plain packaging and up to 5 years in hermetically sealed spaces or Zerust VCI packaging. Axxatec 80C is designed for use on ferrous metals, but may provide some protection to other metals such as aluminum, copper, brass, and nickel alloys, etc. Test before use on non-ferrous metals.

Application Example

A solution of Axxatec 80 is ideal for use with in-line spray or dip applications. The addition rate can be adjusted for a protection period of 6 to 12 months depending on the project requirements.



▶ Benefits

Forms a clear, dry-to-touch, hydrophobic film

Concentrated formula reduces shipping costs and allows for customized dilutable protection

Safe for painted, rubber and plastic materials.

Easy to apply and remove

Non-hazardous*

Application Type

Storage
Shipping
During Operation
May be used with Zerust VCI packaging

*Non-Hazardous Disposal: Product in unopened original container prior to use is non-hazardous waste in the United States according to 40 CFR 261 (no components listed on F, K, P or U lists; not ignitable, not corrosive, not reactive and not toxic).



Use Axxatec 80C for crystal clear, non-tacky water-based protection.

Technical Data

| | | |
|------------------------|--|---|
| Product Info | Water-based rust preventative liquid concentrate. | |
| Application | Apply via immersion, brush, or spray | |
| | Application temperature | 50 to 90°F (10 to 32°C) |
| | Immersion dwell time | 45 s |
| | Drip time | 0 - 15 Min. |
| | Dry time | 45 - 60 mins |
| | Dilution | 2 - 7.5% |
| | Viscosity @ 71°F (21°C) | 650 cps (#63 spindle) @100 rpm |
| | Coverage | 3000 ft ² /279m ² per gal (at 7.5% and drained) |
| | Thickness (varies by method) | 0.25-0.5 mil (6 - 12 µm) |
| Properties | Appearance | Amber liquid |
| | Surface finish | Clear, dry to touch |
| | Removability | Alkaline cleaner |
| | VOC content concentrate | <35% |
| | Freeze and flash point | 32° to 140°F (0° to 62°C) |
| | pH | Approx. 6 - 9 |
| Protection Info | Indoor @ 2% | Up to 6 months |
| | Indoor @ 7.5% | Up to 12 months |
| | Outdoor | Not recommended |
| | Packaging/hermetically sealed | Up to 5 years |
| | Metal types | Ferrous protection, multimetal compatible, not safe for galvanized |
| Storage | Temp | 50 to 90°F (10 to 32°C) |
| | Duration | Up to 2 years |
| Disposal | Dispose of in accordance with local, national and international regulations. | |

Warranty and Disclaimer Information: We guarantee our products conform to documented quality specifications. Product information subject to change without notice. We make no warranty of any kind expressed or implied as to the effects of use (including, but not limited to, damage or injury). For full warranty and disclaimer information visit, www.zerust.com/warranty.

©2015 Northern Technologies International Corporation (NTIC). All Rights Reserved. NTIC is the owner of the following trademarks: ActivPak®, Cor-Tab®, EXCOR®, Flange Saver®, ICT®, NIT®, Plastabs®, Z-CIS®, Zerion®, ZERUST®, The ZERUST People®, and the Color "Yellow". ABRIGO®, UNICO®, and VALENO® are registered trademarks of EXCOR GmbH, a Joint Venture Partner of NTIC.

Contact Us



A product of:
Northern Technologies
International Corp
4201 Woodland Road
Circle Pines, MN 55014
USA

Precautions

- Remove before painting.
- Store in tightly closed container to preserve VCI effectiveness.
- Not for use on galvanized metals.
- Test before use on yellow metals.
- Do not place treated metals in direct contact with cardboard packaging or wood.

Health and Safety

Non-Hazardous Disposal: Product in unopened original container prior to use is non-hazardous waste in the United States according to 40 CFR 261 (no components listed on F, K, P or U lists; not ignitable, not corrosive, not reactive and not toxic).

Availability

Zerust® Axxatec™ 80C is sold as a concentrate.

| Part Number | Qty |
|---------------|--------|
| 350-F-00005PL | 5 Gal |
| 350-F-00005DR | 55 Gal |

Phone. +1 763.225.6600
Fax. +1 763.225.6645
sales@zerust.com
www.zerust.com